

Polietileno PE-1000 Antiestático

General properties	Test method		
Density	DIN EN ISO 1183-1	g/cm ³	0,95
Water absorption	DIN EN ISO 62	%	<0.01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Mechanical properties			
Yield stress	DIN EN ISO 527	N/mm ²	22
Elongation at break	DIN EN ISO 527	%	>200
Tensile modulus of elasticity	DIN EN ISO 527	MPa	700
Notched impact strength (charpy)	DIN EN ISO 179	kJ/m ²	no break
Shore hardness	DIN EN ISO 868	scale D	63
Wear resistance	Sand-slurry		100
Thermal properties			
Melting temperature	ISO 11357-3	°C	135
Thermal conductivity	DIN 52612-1	W/(m*K)	0,40
Thermal capacity	DIN 52612	kJ/(kg*K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ K ⁻¹	150-230
Service temperature, long term	Average	°C	-150...80
Service temperature, short term (max.)	Average	°C	130
Heat deflection temperature	DIN EN ISO 306, Vicat B	°C	79
Electrical properties			
Volume resistivity	IEC 60093	Ω *cm	>10 ⁶
Surface resistivity	IEC 60093	Ω	>10 ⁸

Product characteristics

- Reduction in dust accumulation
- High wear resistance
- High impact strength

Typical field of application

- Mechanical engineering
- Bearing and packing industry
- Electrical and electronic industries

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Los valores e información facilitados son de referencia y orientativos. Se pueden utilizar con fines comparativos para la selección de materiales. Pueden variar en función del proceso. No constituyen una garantía de sus características. Suministros Ind. Azan S.A. no garantiza ni aceptaría ninguna responsabilidad por la exactitud de los mismos.